

STATIC CONTROL PRODUCTS

Non-Skid Backing Floor Mats

POLYMER

NEOPRENE PVC/NITRILE

SPECIFICATIONS

ASTM D 1056-68 _____ SCE 42

ASTM D 1056-85, 91, 98 _____ 2C2

FLAMMABILITY SPECIFICATIONS

UL-94-HF-1 _____ LISTED, >.58"

UL-94-VO _____ LISTED, >.456"

UL-94-HBF _____ PASS

FMVSS-302 _____ PASS

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COMPRESSION DEFLECTION@25%	ASTM D 1056	psi kPa	5.0-9.0 34-62
DENSITY	ASTM D 3575	PCF G/CM?	5.5-7.5 .088-.120
COMPRESSION SET (MAX) BASED ON COMPRESSED HT.	ASTM D 1056	%	35
WATER ABSORPTION MAX. WEIGHT CHANGE	ASTM D 1056	%	5
TEMPERATURE RANGE	N/A	°F	-40 TO +200
TENSILE STRENGTH	ASTM D 412 (DIE A)	psi kPa	75 517
ELONGATION MINIMUM	ASTM D 412 (DIE A)	%	100
HEAT AGING (7 DAYS-158°F) CHANGE IN COMP. DEFL.	ASTM D 1056	%MAX CHANGE	+30
COLOR	N/A	N/A	BLACK

PRODUCT CHARACTERISTICS:

GOOD CHEMICAL RESISTANCE FIRE-RATED CONTINUOUS ROLLS